

**In the Claims:**

Please rewrite the following claims in amended form.

B1

1. (Amended) Textile adhesive tape comprising:  
an adhesive tape support (1), formed by a textile, mechanically reinforced, uninterrupted nonwoven material; and  
an adhesive coating (2) at least at one side of said tape support;  
wherein the nonwoven material has a basis weight of not more than 60 g/m<sup>2</sup> and is impregnated with a thermoplastic resin.

B2

3. (Amended) Adhesive tape according to Claim 1, characterized by the fact that the nonwoven material is reinforced by at least one of air or water jets.

4. (Twice Amended) Adhesive tape according to Claim 1, characterized by the fact that the basis weight of the impregnation is about 1 to 5 g/m<sup>2</sup>.

B3

5. (Twice Amended) Adhesive tape according to Claim 1, characterized by the fact that the nonwoven material comprises viscose fibers, polyester fibers, propylene fibers, or a fiber blend of at least two of the aforementioned fiber materials.

6. (Twice Amended) Adhesive tape according to Claim 1, characterized by the fact that the adhesive coating (2) is a natural rubber adhesive, a synthetic rubber adhesive, an acrylate adhesive, or a UV-crosslinkable acrylate adhesive.

7. (Twice Amended) Adhesive tape according to Claim 1, characterized by the fact that the basis weight of the adhesive coating (2) is about 90 to 150 g/m<sup>2</sup>.

8. (Twice Amended) Adhesive tape according to Claim 1, characterized by the fact that a PET nonwoven having a basis weight of  $40 \text{ g/m}^2$  is used as the textile nonwoven material and that the adhesive coating comprises a synthetic rubber adhesive with a basis weight of  $130 \text{ g/m}^2$ .

9. (Twice Amended) Adhesive tape according to Claim 1, characterized by the fact that the textile nonwoven comprises a PET nonwoven and has a basis weight of  $50 \text{ g/m}^2$  and that the adhesive coating comprises a UV-crosslinkable acrylate adhesive with a basis weight of  $150 \text{ g/m}^2$ .